

POM | KEPITAL F10-02 | Grade

- KEPITAL F10-02 (Rod, Sheet, Tube, Plate) Grade .

- Porosity White Mark .

	ISO 1043	-	POM
--	----------	---	-----

(23 , 50 %RH)	ISO 62	%	0.2
	ISO 1183	g/cm ³	1.41
	ISO 1133	g/10min	3.0

(1.8 MPa)	ISO 75		96
	UL 94	-	HB
	ISO 11359	X 10 ⁻⁵ /	12
	ISO 11357		165

	ISO 527	MPa	2,600
	ISO 527	MPa	63
	ISO 527	%	10
	ISO 527	%	32
	ISO 178	MPa	84
	ISO 178	MPa	2,400
Charpy (Notched, 23)	ISO 179/1eA	kJ/m ²	8.0
Charpy (Notched, -30)	ISO 179/1eA	kJ/m ²	6.5

	IEC 60093		1x10 ¹⁶
	IEC 60093	• cm	1x10 ¹⁴
	IEC 60243-1	kV/mm	19

(, t = 2 mm)	ISO 294-4	%	2.0
---------------	-----------	---	-----

Revision No : 6 (2019-09-17)

